



AGS COMPANY

P.O. Box 729
 Muskegon, MI 49443
 231-733-2101 Fax: 231-733-1784
 info@agscompany.com

DOOR-EASE STICK LUBRICANT

DESCRIPTION: The material covered by this specification is a solidified lubricant, molded in stick form. It consists of a specially-blended wax composition, plasticized with mineral oil, and containing film strength additives. Composition does not dry out, exude oil, or crumble, and is sufficiently dry to prevent catching excessive dirt and dust under normal conditions.

APPLICATION Used for lubrication of exposed friction surfaces. Facilitates assembly of various parts. When applied to metal, wood, rubber, plastic, glass, and other surfaces, prevents squeaks, wear, and sticking. DOOR-EASE is used like a crayon in application to surfaces. It can also be applied by melting in a glue pot or similar equipment. Apply molten DOOR-EASE by dipping, brushing, or with saturated cloth.

Packaging Universal Size - approximately 1/2" diameter x 4-3/8" long
 Shop Size - approximately 1" diameter x 4-3/8" long

- DE-1
- DE-2
- DE-3
- DE-25 25 pound block
- DEB-2
- DEB-3
- DEK-3
- DEP-1
- DEK-3SP
- DKC-3
- DEK-3H

| | | |
|-------------------|---------------------------------------|------------------------------|
| Properties | Appearance and Color | Light Tan Solid |
| | Texture | Microcrystalline |
| | ASTM Penetration @ 77°F (50g. Needle) | 5.0 - 10 mm |
| | ASTM melting Point | 150°F +/- 5° |
| | Moisture | Nil |
| | Ash (as Sulfate) | Nil |
| | Free Alkali (as NaOH) | Nil |
| | Film Strength (Falex test): | 700 to 800 pound Jaw Load |
| | Test Pins | Vee Blocks |
| | SAE 3135 Steel | AISI 1137 Steel |
| | Hardness Rb 87-91 | Hardness Rc 20-24 |
| | Surface Finish - 10 RMS max. | Surface Finish - 10 RMS max. |
| | Meets Chrysler standard MS-1481 | |

P.O. Box 729, Muskegon, MI 49443, U.S.A.
 Toll Free 800-253-0403 Toll Free in Michigan Canada 800-735-0403
 Local Calls (231) 733-2101 FAX (231) 733-1784